

SMS COVERALL

PRODUCT CODE: DOWSMS | DOBSMS | DOOSMS

DESCRIPTION

SMS Coverall with Triple Layer Polypropylene

FEATURES AND BENEFITS

Lightweight and soft with excellent strength

Elasticated wrists and ankles

Zip Seal for increased particle protection

Excellent breathability to reduce moisture build up

Excellent barrier to dust and light splash

Lint-free

Good opacity

Two way zipper for when nature calls

Ready access to clothing underneath

Sold and packaged individually

PRODUCT DETAILS

Materials : SMS (Spunbond, Meltblown, Spunbond Triple Layer Polypropylene)

Colour : White, Orange, Blue

Fabric GSM : 50GSM

Sizes : M (168-176cm x 92-100cm);
L (174-182cm x 100-108cm);
XL (180-188cm x 108-116cm);
2XL (186-194cm x 116-124cm);
3XL (192-200cm x 124-132cm)

Qty/Carton : 50

Nonwoven outer layer



Meltblown layer

Nonwoven inner layer

STANDARDS

CE CATEGORY: Type 5 - Particle Tight Clothing
Type 6 - Limited Splash Particle Tight Clothing

Other Colours



Blue



Orange

DOBSMS - Blue

DOOSMS - Orange



PRODUCT CODE : DOWSMS



Type 5



Type 6

WA

T (618) 9301 7888
F (618) 9310 7889
E wa@paramountsafety.com.au

MELBOURNE

T (613) 9764 9900
F (613) 9764 9800
E vic@paramountsafety.com.au

SYDNEY

T (612) 9601 3877
F (612) 9601 3899
E nsw@paramountsafety.com.au

BRISBANE

T (617) 3806 2699
F (617) 3806 3266
E qld@paramountsafety.com.au

ADELAIDE

M 0424 504 802
T (613) 9764 9900
F (613) 9764 9800
E sa@paramountsafety.com.au

NEW ZEALAND

T (649) 525 8090
F (649) 523 9773
E nz@paramountsafety.co.nz

 STANDARDS

CE CATEGORY: Chemical Protective Clothing III
 Type 5 - Particle Tight Clothing
 Type 6 - Limited Splash Particle Tight Clothing

Performance Classification of Materials			
Abrasion Resistance	EN 530 Method 2	10 C cycles (Visual Assessment)	1
Flex Cracking Resistance	ISO 7854 Method B	10000 C cycles (Visual Assessment)	4
Trapezoidal Tear Resistance	ISO 9073-4	MD 39.6 N CD 23.6 N	2
Tensile Strength	ISO 13934-1	MD 83.6 N CD 51.0 N	1
Puncture Resistance	EN863	6.22 N	2
Repellency to Liquids - EN368			
30% H ₂ SO ₄	98.2%	3	
10% NaOH	97.5%	3	
o-Xylene	90.6%	2	
Butan-1-ol	95.1%	3	
Resistance to Penetration by Liquids - EN368			
30% H ₂ SO ₄	0.0%	3	
10% NaOH	0.0%	3	
o-Xylene	0.0%	3	
Butan-1-ol	0.0%	3	

WA

T [618] 9301 7888
 F [618] 9310 7889
 E wa@paramountsafety.com.au

MELBOURNE

T [613] 9764 9900
 F [613] 9764 9800
 E vic@paramountsafety.com.au

SYDNEY

T [612] 9601 3877
 F [612] 9601 3899
 E nsw@paramountsafety.com.au

BRISBANE

T [617] 3806 2699
 F [617] 3806 3266
 E qld@paramountsafety.com.au

ADELAIDE

M 0424 504 802
 T [613] 9764 9900
 F [613] 9764 9800
 E sa@paramountsafety.com.au

NEW ZEALAND

T [649] 525 8090
 F [649] 523 9773
 E nz@paramountsafety.co.nz